

Technical Data Sheet – ASTM Standard

Lundhs Marina

Lundhs Marina is characterised by large steel-blue feldspar crystals.

Technical Properties	Standard	Mean Values
stone name:		monzonite (larvikite)
structure:		coarse grained
texture:		oriented feldspar crystals with lustre
Compressive Strength	ASTM C-170	31,428 PSI
Flexural Strength	ASTM C-880	1,739 PSI
Abrasion Resistance	ASTM C-1353	261.5 wear index value
Water Absorption	ASTM C-97	0.18 %
Density	ASTM C-97	171.4 lb/ft ²
Modulus of Rupture	ASTM C-99	2,534 PSI
petrographic composition:		feldspar 85% pyroxene 4% olivine 2% amphibole 3% nepheline 2% magnetite 2% apatite 1% biotite 1%

* PSI: Pounds Per Square Inch

** Method: American Society for Testing and Materials

Source: ABIC Testing Laboratories, Inc.

Box 2051, Stubberud
N-3255 Larvik, Norway

Telephone: +47 33 12 11 64
 Fax: +47 33 18 23 34
 Email: info@lundhs.no
www.lundhs.no